

COLLECTION: BILBAO (MERCIS)

DESIGN: BILBAO (MERCIS)

BASIC INFORMATION

Brand	Mercis	Number of colour ways	29
Tariff item number	5801360000	MID	SIMER3RAD
Country of origin	China	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	0
Full roll diameter inch	0	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex 164683	Yes
-----------------	-----

**PFC
FREE**

Labels

There are no technical details for this section.

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
EN 1021-1	Yes	FMVSS 302	Yes
NFPA 260	Yes		

COLLECTION: BILBAO (MERCIS)

DESIGN: BILBAO (MERCIS)

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	0
Woven	Yes	Embroidery width cm	0
Embroidery Width Inch	0	Useable width cm	143
Useable width inch	56.3	Full width cm	145
Full width inch	57.09	Weight g/m²	505
Thickness mm	0.000	Colouring type	Piece dyed
Water repellent	Yes		

Treatment

There are no technical details for this section.

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Plain	Yes
-------	-----

COLLECTION: BILBAO (MERCIS)

DESIGN: BILBAO (MERCIS)

MECHANICAL PERFORMANCE

Martindale rubs	50,000	Colour fastness to light	8
Wyzenbeek double rubs	100,000	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Water repellent	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light – ISO 105-B02

Colour fastness to light	8
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

There are no technical details for this section.

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	96	Tearing strength weft N	110
-------------------------	----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1600	Tensile strength weft N/5cm	1100
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

There are no technical details for this section.

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	0.00

COLLECTION: BILBAO (MERCIS)

DESIGN: BILBAO (MERCIS)

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.29	Dimensional change warp after ironing	-1.39
Dimensional change weft	-1.66	Dimensional change weft after ironing	-1.66

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

CONSTRUCTION

There are no technical details for this section.

Full technical product specifications (TPS) for this design

COLLECTION: BILBAO (MERCIS)

DESIGN: BILBAO (MERCIS)

DOWNLOADS

There are no technical details for this section.