

COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	32
Tariff item number	5514230000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	0	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

FABRIC SPECIFICATIONS

Composition	64% Polyester, 32% Viscose, 4% Cotton	Average yarn number	8.03
Construction	25.18x12.58	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m²	470	Thickness mm	1.360
Colouring type	Piece dyed	Water repellent	Yes
Filament or staple	32% Filament, 68% Staple	Textured or non textured	32% Textured, 68% Not textured

Treatment

Backing	Yes	Stain free technology	Yes
---------	-----	-----------------------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes	Reactive	Yes
----------	-----	----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

MECHANICAL PERFORMANCE

Martindale rubs	30,000	Colour fastness to light	4
Wyzenbeek double rubs	200,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Water repellent	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	160	Tearing strength weft N	220
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1500	Tensile strength weft N/5cm	840
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	31,5	Elongation weft %	25,5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.13	Dimensional change warp after ironing with steam	-0.21
Dimensional change warp after ironing without steam	-0.10	Dimensional change weft	-0.07
Dimensional change weft after ironing with steam	-0.08	Dimensional change weft after ironing without steam	-0.08

COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.59	Dimensional change warp after ironing	-1.13
Dimensional change weft	-1.03	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.35	Dimensional change warp after ironing	-3.38
Dimensional change weft	-2.09	Dimensional change weft after ironing	-2.06
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.79	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.56	Dimensional change weft after ironing	-0.46
Colour fastness ISO 105 D01	4-5		

COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	300D/96	Warp Textured	Yes
Warp Threads per cm	18.89	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300D/96	Weft Textured	Yes
Weft Threads per cm	8.38	Weft TPM	0

Yarn 3

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	3.5NM	Warp Textured	Yes
Warp Threads per cm	6.29	Warp TPM	0

Yarn 4

Weft Composition	62% Viscose, 38% Cotton	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	6NM	Weft Textured	No
Weft Threads per cm	2.12	Weft TPM	0

Yarn 5

Weft Composition	56% Polyester, 44% Viscose	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	3.5NM	Weft Textured	Yes
Weft Threads per cm	2.08	Weft TPM	0

DOWNLOADS

-  [Bouclette – FibreGuard report](#)
-  [Bouclette -NFPA 260_UFAC-21004](#)

-  [Bouclette -FMVSS302-21004](#)
-  [Bouclette -Cal TB 117-2013-21004](#)



COLLECTION: BOUCLETTE

DESIGN: BOUCLETTE

