

COLLECTION: BRUGGE

DESIGN: BRUGGE

BASIC INFORMATION

Brand	Bru	Number of colour ways	30
Tariff item number	5309190000	MID	TRMAR3INE
Country of origin	Turkey	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	20
Full roll diameter inch	7.87	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments

Iron with steam

Use codes

Curtains	Yes	Curtains and draperies	Yes
Bed covering	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

There are no technical details for this section.

COLLECTION: BRUGGE

DESIGN: BRUGGE

FR STANDARDS

CAL 117	No	FMVSS 302	Yes
NFPA 260	Yes		

FABRIC SPECIFICATIONS

Composition	100% Linen	Average yarn number	8.13
Construction	16x10	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	320	Thickness mm	0.900
Colouring type	Piece dyed	Filament or staple	100% Staple
Textured or non textured	100% not textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Airo	Yes
------	-----

Type of print or dye

Reactive	Yes
----------	-----

Weaving type

Plain	Yes
-------	-----

COLLECTION: BRUGGE

DESIGN: BRUGGE

MECHANICAL PERFORMANCE

Martindale rubs	10,000	Colour fastness to light	5
Wyzenbeek double rubs	5,000	Pilling	3
Brush pilling	3	Wyzenbeek wire screen double rubs	6,000
Wyzenbeek cotton duck double rubs	5,000	Wyzenbeek cotton duck type unrated	Yes
Wyzenbeek wire screen unrated	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	270	Tearing strength weft N	190
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	790	Tensile strength weft N/5cm	1300
-----------------------------	-----	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	15	Elongation weft %	16
-------------------	----	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	16	Seam slippage weft mm	6
-----------------------	----	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.17	Dimensional change warp after ironing with steam	0.73
Dimensional change warp after ironing without steam	0.40	Dimensional change weft	0.08
Dimensional change weft after ironing with steam	0.53	Dimensional change weft after ironing without steam	0.27

COLLECTION: BRUGGE

DESIGN: BRUGGE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.09	Dimensional change warp after ironing	-2.52
Dimensional change weft	-3.00	Dimensional change weft after ironing	-3.00
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.78	Dimensional change warp after ironing	-2.38
Dimensional change weft	-4.87	Dimensional change weft after ironing	-4.57
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-1.33
Dimensional change weft	-1.46	Dimensional change weft after ironing	-1.33
Colour fastness ISO 105 D01	4-5		

COLLECTION: BRUGGE

DESIGN: BRUGGE

CONSTRUCTION

Yarn 1

Warp Composition	100% Linen	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	16NM	Warp Textured	No
Warp Threads per cm	16	Warp TPM	0

Yarn 2

Weft Composition	100% Linen	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1800 DN	Weft Textured	No
Weft Threads per cm	10	Weft TPM	0

DOWNLOADS

-  [Brugge](#)
-  [Brugge-NFPA 260_UFAC](#)
-  [Brugge-FMVSS302](#)
-  [Brugge](#)

