

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	38
Tariff item number	5514230000	MID	INDDEEXP167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	40
Minimum for special colour m	0	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

There are no technical details for this section.

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	No
CAL 117	Yes	EN 1021-1	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	73% Polyester, 27% Cotton	Average yarn number	9.25
Construction	20.5x19	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	427	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

There are no technical details for this section.

Weaving type

Dobby	Yes
-------	-----

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	90,000	Pilling	3-4
Brush pilling	3-4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	90,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	200	Tearing strength weft N	240
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	840
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	32.5	Elongation weft %	30.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.19	Dimensional change warp after ironing with steam	-0.13
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.60	Dimensional change weft after ironing without steam	0.00

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.80
Dimensional change weft	-0.63	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.96	Dimensional change warp after ironing	-1.79
Dimensional change weft	-0.80	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	0.37	Dimensional change warp after ironing	0.33
Dimensional change weft	-0.10	Dimensional change weft after ironing	0.33
Colour fastness ISO 105 D01	4-5		

COLLECTION: COLOURWASH

DESIGN: COLOURWASH

CONSTRUCTION

Yarn 1

Warp Composition	85% Polyester, 15% Cotton	Warp Is Filament	No
Warp Is Not High Tenacity	No	Warp Is Staple	Yes
Warp Sizes	2/16	Warp Textured	No
Warp Threads per cm	20.5	Warp TPM	500

Yarn 2

Weft Composition	55% Polyester, 45% Cotton	Weft Is Filament	No
Weft Is Not High Tenacity	No	Weft Is Staple	Yes
Weft Sizes	2/10	Weft Textured	No
Weft Threads per cm	19	Weft TPM	210

DOWNLOADS

-  [COLOURWASH ECO-Cal TB 117-2013-47733](#)
-  [COLOURWASH ECO-FMVSS302-47733](#)
-  [Colourwash-NFPA 260 UFAC](#)
-  [COLOURWASH ECO-NFPA 260 24-47733](#)
-  [Colourwash EN 1021-1](#)

-  [Colourwash-Cal TB 117-2013](#)
-  [Colourwash – FibreGuard report](#)
-  [Colourwash Eco 25010439A Bru Textiles BS5825 Source 0](#)
-  [Colourwash-FMVSS302](#)

