

COLLECTION: COVERLET

DESIGN: COVERLET

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	30
Tariff item number	5801360000	MID	CNTONFOR1202TON
Country of origin	China	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	29
Full roll diameter inch	11.42	Average piece length m	40
Minimum for special colour m	0	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



**STANDARD
100**
0611045
Centexbel

**PFC
FREE**

ISO 14001
Environmental
Management

Labels

Prop 65	Yes
---------	-----

COLLECTION: COVERLET

DESIGN: COVERLET

FR STANDARDS

AS/NZS 1530.3	Yes	BS 5852 Source 0	Yes
BS 5852 Source 1 (with treatment)	Yes	CAL 117	Yes
EN 1021-2 (with treatment)	Yes	FMVSS 302	Yes
NFPA 260	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	23.94
Construction	64x17.4	Woven	Yes
Useable width cm	142	Useable width inch	55.91
Full width cm	144	Full width inch	56.69
Weight g/m²	340	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	33% filament / 67% staple
Textured or non textured	33% textured / 67% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Vat	Yes
-----	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: COVERLET

DESIGN: COVERLET

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Colour fastness to light	5
Wyzenbeek double rubs	60,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	60,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	71	Tearing strength weft N	110
-------------------------	----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1600	Tensile strength weft N/5cm	990
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	38	Elongation weft %	19.50
-------------------	----	-------------------	-------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.12	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	-0.53	Dimensional change weft after ironing without steam	0.00

COLLECTION: COVERLET

DESIGN: COVERLET

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.36	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.43	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.12	Dimensional change warp after ironing	-1.06
Dimensional change weft	-1.36	Dimensional change weft after ironing	-1.32
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.63	Dimensional change warp after ironing	-0.73
Dimensional change weft	-1.36	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 D01	4-5		

COLLECTION: COVERLET

DESIGN: COVERLET

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	No	Warp Is Staple	No
Warp Sizes	150D	Warp Textured	Yes
Warp Threads per cm	64	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	No	Weft Is Staple	Yes
Weft Sizes	300D	Weft Textured	No
Weft Threads per cm	8.7	Weft TPM	0

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	No	Weft Is Staple	Yes
Weft Sizes	5.3S	Weft Textured	Yes
Weft Threads per cm	8.7	Weft TPM	0

DOWNLOADS

[Coverlet Fabric Cert Fire Retardant AS 1530.3](#)
[Coverlet Bru Textiles BS 5852 Source 0](#)
[Coverlet -NFPA 260 UFAC-20779](#)
[Coverlet EN 1021-1](#)
[Coverlet -Cal TB 117-2013-20779](#)
[Coverlet – FibreGuard report](#)
[Coverlet -FMVSS302-20779](#)
