

COLLECTION: CUDDLY

DESIGN: CUDDLY

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	30
Tariff item number	5801360000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	25
Full roll diameter inch	9.84	Average piece length m	25
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Care code comments

Iron on reverse side

Use codes

Upholstery

Yes

Accessories

Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65

Yes

COLLECTION: CUDDLY

DESIGN: CUDDLY

FR STANDARDS

AS/NZS 1530.3	Yes	BS 5852 Source 0	Yes
BS 5852 Source 1 (with treatment)	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	93% Polyester, 7% Cotton	Average yarn number	11.66
Construction	64,57x11,82	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m²	655	Thickness mm	1.730
Colouring type	Yarn dyed	Filament or staple	86% Filament, 14% Staple
Textured or non textured	86% Textured, 14% Not Texture		

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes

Type of finish

Airo	Yes
------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: CUDDLY

DESIGN: CUDDLY

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	5-6
Wyzenbeek double rubs	100,000	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen medium duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	110	Tearing strength weft N	140
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1900	Tensile strength weft N/5cm	550
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	46.5	Elongation weft %	26
-------------------	------	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	3	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

There are no technical details for this section.

COLLECTION: CUDDLY

DESIGN: CUDDLY

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-4.00	Dimensional change warp after ironing	0.00
Dimensional change weft	-8.50	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

There are no technical details for this section.

COLLECTION: CUDDLY

DESIGN: CUDDLY

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	155/34/450 Poly tex	Warp Textured	Yes
Warp Threads per cm	64.57	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300D Grey Rotto	Weft Textured	Yes
Weft Threads per cm	3.94	Weft TPM	0

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	3.5NM DD Chenille	Weft Textured	No
Weft Threads per cm	3.94	Weft TPM	0

Yarn 4

Weft Composition	83% Polyester, 17% Cotton	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1.3NM DD Chenille	Weft Textured	Yes
Weft Threads per cm	3.94	Weft TPM	0

DOWNLOADS

-  [Cuddly-FMVSS302-33772](#)
-  [Cuddly - FibreGuard report](#)
-  [Cuddly-NFPA 260 UFAC-33772](#)

-  [Cuddly BS 5852 Source 0](#)
-  [Cuddly-Cal TB 117-2013-33772](#)



