

COLLECTION: DELUXE

DESIGN: DELUXE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	53
Tariff item number	6001920000	MID	CNJIABRI366TON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	25
Full roll diameter inch	9.84	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments

Iron on reverse side

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

There are no technical details for this section.

COLLECTION: DELUXE

DESIGN: DELUXE

FR STANDARDS

AS/NZS 1530.3	Yes	BS 5852 Source 0	Yes
BS 5852 Source 1 (with treatment)	Yes	CAL 117	Yes
EN 1021-2 (with treatment)	Yes	FMVSS 302	Yes
NFPA 260	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	30.77
Construction	knitted	Useable width cm	141
Useable width inch	55.51	Full width cm	143
Full width inch	56.3	Weight g/m ²	455
Thickness mm	1.190	Colouring type	Printed
Filament or staple	100% filament	Textured or non textured	100% not textured
Knitted	Yes		

Treatment

Backing	Yes	Stain free technology	Yes
---------	-----	-----------------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Pile	Yes
------	-----

COLLECTION: DELUXE

DESIGN: DELUXE

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	200,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4
-------------------------	---

Tearing strength – ISO 13937-3

Tearing strength warp N	75	Tearing strength weft N	82
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	560	Tensile strength weft N/5cm	630
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	42	Elongation weft %	17
-------------------	----	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.12	Dimensional change warp after ironing with steam	0.33
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.27	Dimensional change weft after ironing without steam	0.07

COLLECTION: DELUXE

DESIGN: DELUXE

ACOUSTICS

Sound absorption performance for drapery

Weighted Sound Absorption Coefficient (α_w) – ISO 11654	0.75	Weighted Sound Absorption Coefficient (α_w) – Class – ISO 11654	C
Sound Absorption Average ($\bar{\alpha}$) – ASTM C423	0.78	Noise Reduction Coefficient (NRC) – ASTM C423	0.85

Sound absorption performance for upholstery

Weighted Sound Absorption Coefficient (α_w) – ISO 11654	0.7	Weighted Sound Absorption Coefficient (α_w) – Class – ISO 11654	C
Sound Absorption Average ($\bar{\alpha}$) – ASTM C423	0.7	Noise Reduction Coefficient (NRC) – ASTM C423	0.7

Sound transmission

Weighted Sound Reduction Index (RW) – ISO 717-1	6	Sound Transmission Class (STC) – ASTM E413	6
---	---	--	---

WASHABILITY

Resistance to domestic washing 30° C, indicated in % – ISO 6330

Dimensional change warp	-0.17	Dimensional change warp after ironing	-0.13
Dimensional change weft	0.13	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % – ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % – ISO 6330

Dimensional change warp	-1.30	Dimensional change warp after ironing	-1.19
Dimensional change weft	0.03	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % – ISO 105 D01

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.10	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 D01	5		

COLLECTION: DELUXE

DESIGN: DELUXE

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	105d	Weft Textured	No
Weft Threads per cm	50	Weft TPM	300

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	105d	Warp Textured	No
Warp Threads per cm	90	Warp TPM	200

DOWNLOADS

 202501760-Acoustics_Deluxe	 Deluxe - EN1021 1+2
 202501760-Acoustic_Deluxe	 Deluxe EN 1021-1
Combo, Deluxe, Diana, Impact, Indulge, Bolt-Textile Testing Submittal	
 Form Rev. F (2) - Copy	 Deluxe-NFPA 260 UFAC
 Deluxe-FMVSS302	 Deluxe-Cal TB 117-2013-46434
 DELUXE-NFPA 260 UFAC-46434	 Deluxe - BS5852 source 0
 Deluxe-Cal TB 117-2013	 Deluxe-E84 Unadhered-25776
 Deluxe BS 5852 Sources 0+1	 Deluxe - FibreGuard report
 Deluxe Fabric Cert Fire Retardant AS 1530.3	 Deluxe
 Deluxe NFPASM99-1	 Deluxe-NFPA 260 UFAC-46434



