

COLLECTION: DRAMA

DESIGN: DRAMA

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	51
Tariff item number	5801360000	MID	TRKET40IST
Country of origin	Turkey	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	28
Full roll diameter inch	11.02	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Care code comments iron on reverse side

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65 Yes

COLLECTION: DRAMA

DESIGN: DRAMA

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	50% Acrylic, 45% Polyester, 5% Viscose	Average yarn number	9.55
Construction	35x5	Woven	Yes
Useable width cm	142	Useable width inch	55.91
Full width cm	144	Full width inch	56.69
Weight g/m²	419	Thickness mm	1.380
Colouring type	Yarn dyed	Filament or staple	71% staple + 29% filament
Textured or non textured	100% textured		

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Plain	Yes
-------	-----

COLLECTION: DRAMA

DESIGN: DRAMA

MECHANICAL PERFORMANCE

Martindale rubs	90,000	Colour fastness to light	4-5
Wyzenbeek double rubs	35,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	35,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4-5
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Tearing strength – ISO 13937-3

Tearing strength warp N	29	Tearing strength weft N	100
-------------------------	----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	630
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	46.5	Elongation weft %	15.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.10	Dimensional change warp after ironing with steam	-0.73
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.15
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	-1.67

COLLECTION: DRAMA

DESIGN: DRAMA

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.13	Dimensional change warp after ironing	-1.12
Dimensional change weft	-2.98	Dimensional change weft after ironing	-2.92
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.75	Dimensional change warp after ironing	-2.58
Dimensional change weft	-5.13	Dimensional change weft after ironing	-4.90
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.99
Dimensional change weft	-1.09	Dimensional change weft after ironing	-0.99
Colour fastness ISO 105 D01	4-5		

COLLECTION: DRAMA

DESIGN: DRAMA

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	150 Den	Warp Textured	Yes
Warp Threads per cm	35	Warp TPM	350

Yarn 2

Weft Composition	70% Acrylic, 18% Polyester, 12% Viscose	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	3.8NM	Weft Textured	Yes
Weft Threads per cm	5	Weft TPM	0

DOWNLOADS

-  [Drama-Cal TB 117-2013-33268](#)
-  [Drama-FMVSS302-33268](#)
-  [Drama-NFPA 260 UFAC-33268](#)

-  [Drama BS 5852 Source 0](#)
-  [Drama - FibreGuard report](#)
-  [Drama - Anti-bacterial report](#)

