

COLLECTION: EARTHWILD

DESIGN: EARTHWILD

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	33
Tariff item number	5514230000	MID	INDDEEXP167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	28
Full roll diameter inch	11.02	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD 100
2111231
Centexbel



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

COLLECTION: EARTHWILD

DESIGN: EARTHWILD

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	65% Recycled Polyester, 32% Organic Cotton, 3% Linen	Average yarn number	6.48
Construction	16.5x17.2	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	520	Thickness mm	1.310
Colouring type	Piece dyed	Filament or staple	73% staple + 27% filament
Textured or non textured	60% textured + 40% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: EARTHWILD

DESIGN: EARTHWILD

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	5
Wyzenbeek double rubs	82,500	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	82,500	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Tearing strength – ISO 13937-3

Tearing strength warp N	160	Tearing strength weft N	310
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	890	Tensile strength weft N/5cm	970
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	22.5	Elongation weft %	32.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.12	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.78
Dimensional change weft after ironing with steam	0.94	Dimensional change weft after ironing without steam	0.00

COLLECTION: EARTHWILD

DESIGN: EARTHWILD

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.03	Dimensional change warp after ironing	-0.93
Dimensional change weft	-0.86	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.92	Dimensional change warp after ironing	-1.72
Dimensional change weft	-1.26	Dimensional change weft after ironing	-1.13
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-3.00	Dimensional change warp after ironing	0.00
Dimensional change weft	-3.30	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.99	Dimensional change warp after ironing	-0.53
Dimensional change weft	-0.73	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 D01	5		

COLLECTION: EARTHWILD

DESIGN: EARTHWILD

CONSTRUCTION

Yarn 1

Warp Composition	56% Recycled Polyester, 44% Organic Cotton	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2.2NM	Warp Textured	No
Warp Threads per cm	4.1	Warp TPM	480

Yarn 2

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	300 Roto	Warp Textured	Yes
Warp Threads per cm	12.4	Warp TPM	0

Yarn 3

Weft Composition	40% Recycled Polyester, 42% Organic Cotton, 18% Linen	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	4.5 NM	Weft Textured	No
Weft Threads per cm	5.7	Weft TPM	480

Yarn 4

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300 Roto	Weft Textured	Yes
Weft Threads per cm	11.5	Weft TPM	0

DOWNLOADS

-  [Earthwild-NFPA 260_UFAC-35438](#)
-  [Earthwild BS 5852 Source 0](#)
-  [202600539-Acoustic_Earthcore](#)

-  [Earthwild - FibreGuard report](#)
-  [Earthwild-FMVSS302-35438](#)
-  [Earthwild-Cal TB 117-2013-35438](#)



