

COLLECTION: ECO STRIPE

DESIGN: ECO STRIPE

BASIC INFORMATION

Brand	Bru	Number of colour ways	29
Tariff item number	5515129000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Flat Weave
Vertical repeat cm	Stripe	Vertical repeat inch	Stripe
Horizontal repeat cm	20.00	Horizontal repeat inch	7.87
Face in	Yes	Full roll diameter cm	16
Full roll diameter inch	6.3	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

COLLECTION: ECO STRIPE

DESIGN: ECO STRIPE

FR STANDARDS

BS 5867 part 2 type B	Yes	BS 5852 Source 0	Yes
CAL 117	Yes	CAN/ULC S109 large flame	Yes
CAN/ULC S109 small flame	Yes	FMVSS 302	Yes
NFPA 260	Yes	NFPA 701	Yes

FABRIC SPECIFICATIONS

Composition	100% Recycled Polyester	Average yarn number	64.51
Construction	108.27x29.13	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m²	213	Thickness mm	0.410
Colouring type	Yarn dyed	Filament or staple	58% staple, 42% filament
Textured or non textured	58% not textured, 42% textured		

Treatment

Flame retardant	Yes
-----------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: ECO STRIPE

DESIGN: ECO STRIPE

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Colour fastness to light	4
Wyzenbeek double rubs	60,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	60,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen medium duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Tearing strength – ISO 13937-3

Tearing strength warp N	110	Tearing strength weft N	43
-------------------------	-----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1300	Tensile strength weft N/5cm	2100
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	41	Elongation weft %	19
-------------------	----	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.02	Dimensional change warp after ironing with steam	-0.40
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	0.00

COLLECTION: ECO STRIPE

DESIGN: ECO STRIPE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.50	Dimensional change warp after ironing	-0.53
Dimensional change weft	0.10	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.16	Dimensional change warp after ironing	-1.20
Dimensional change weft	0.17	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-2.60	Dimensional change warp after ironing	0.00
Dimensional change weft	0.50	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.73	Dimensional change warp after ironing	0.13
Dimensional change weft	0.03	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 D01	4-5		

COLLECTION: ECO STRIPE

DESIGN: ECO STRIPE

CONSTRUCTION

Yarn 1

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	65/36/500	Warp Textured	Yes
Warp Threads per cm	54.33	Warp TPM	500

Yarn 2

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	65/36/500	Warp Textured	Yes
Warp Threads per cm	53.94	Warp TPM	500

Yarn 3

Weft Composition	100% Recycled Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	2/30'S	Weft Textured	No
Weft Threads per cm	29.13	Weft TPM	0

DOWNLOADS

 [Eco Stripe-NFPA 260 UFAC-43447](#) [Eco Stripe - BSB5867](#) [Eco Stripe BS5825 Source 0](#) [Eco Stripe-FMVSS302-43447](#) [Eco Stripe-CAN ULC S109-44291](#) [202302931-NFPA701 Eco Stripe](#) [Eco Stripe-Cal TB 117-2013-43447](#)