

COLLECTION: FOOTLOOSE

DESIGN: FOOTLOOSE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	28
Tariff item number	5801360000	MID	TRKET40IST
Country of origin	Turkey	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	29
Full roll diameter inch	11.42	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Accessories	Yes
------------	-----	-------------	-----

ENVIRONMENTAL STANDARDS



STANDARD 100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	No
CAL 117	Yes	FMVSS 302	Yes
NFPA 260	Yes		

COLLECTION: FOOTLOOSE

DESIGN: FOOTLOOSE

FABRIC SPECIFICATIONS

Composition	50% Polyester, 50% Acrylic	Average yarn number	22.7
Construction	66x30	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m²	423	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	42% filament, 58% staple
Textured or non textured	42% textured, 58% not textured		

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Plain	Yes
-------	-----

COLLECTION: FOOTLOOSE

DESIGN: FOOTLOOSE

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	4-5
Wyzenbeek double rubs	98,800	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	98,800	Wyzenbeek cotton duck type general upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4-5
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	120	Tearing strength weft N	100
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	2100	Tensile strength weft N/5cm	810
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	44	Elongation weft %	15.5
-------------------	----	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.21	Dimensional change warp after ironing with steam	0.07
Dimensional change warp after ironing without steam	0.20	Dimensional change weft	-0.15
Dimensional change weft after ironing with steam	-0.20	Dimensional change weft after ironing without steam	0.00

COLLECTION: FOOTLOOSE

DESIGN: FOOTLOOSE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.17	Dimensional change warp after ironing	-0.26
Dimensional change weft	-0.46	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-0.73	Dimensional change warp after ironing	-0.59
Dimensional change weft	-1.32	Dimensional change weft after ironing	-1.32
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-2.00	Dimensional change warp after ironing	0.00
Dimensional change weft	-3.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.53	Dimensional change warp after ironing	-0.79
Dimensional change weft	-0.83	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 D01	4-5		

COLLECTION: FOOTLOOSE

DESIGN: FOOTLOOSE

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	150 den	Warp Textured	Yes
Warp Threads per cm	66	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	500 den	Weft Textured	Yes
Weft Threads per cm	15	Weft TPM	0

Yarn 3

Weft Composition	90% Viscose, 10% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1.45 nm	Weft Textured	No
Weft Threads per cm	15	Weft TPM	0

DOWNLOADS

-  [Footloose - Anti-bacterial report](#)
-  [Footloose-NFPA 260 UFAC-32878](#)
-  [Footloose-Cal TB 117-2013-32878](#)

-  [Footloose - FibreGuard report](#)
-  [Footloose - BS 5852 Source 0](#)
-  [Footloose-FMVSS302-32878](#)

