

COLLECTION: GIANT

DESIGN: GIANT

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	40
Tariff item number	5801360000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	30.2
Full roll diameter inch	11.89	Average piece length m	40
Minimum for special colour m	0	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



**STANDARD
100**
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

COLLECTION: GIANT

DESIGN: GIANT

FR STANDARDS

AS/NZS 1530.3	Yes	BS 5852 Source 0	Yes
BS 5852 Source 1 (with treatment)	Yes	CAL 117	Yes
EN 1021-1	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes
NFPA 701	No		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	4.42
Construction	12.60x7.48	Woven	Yes
Useable width cm	139	Useable width inch	54.72
Full width cm	141	Full width inch	55.51
Weight g/m²	454	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	68% filament, 32% staple
Textured or non textured	100% not textured		

Treatment

Backing	Yes	Stain free technology	Yes
---------	-----	-----------------------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: GIANT

DESIGN: GIANT

MECHANICAL PERFORMANCE

Martindale rubs	30,000	Colour fastness to light	5-6
Wyzenbeek double rubs	200,000	Pilling	4
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	46	Tearing strength weft N	88
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1200	Tensile strength weft N/5cm	660
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	27	Elongation weft %	18.50
-------------------	----	-------------------	-------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.08
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	0.00

COLLECTION: GIANT

DESIGN: GIANT

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.56	Dimensional change warp after ironing	-0.66
Dimensional change weft	0.00	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.58	Dimensional change warp after ironing	-2.45
Dimensional change weft	-0.17	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.91	Dimensional change warp after ironing	-0.07
Dimensional change weft	-0.13	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 D01	5		

COLLECTION: GIANT

DESIGN: GIANT

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	5nm	Warp Textured	No
Warp Threads per cm	12.6	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	5nm	Weft Textured	No
Weft Threads per cm	7.48	Weft TPM	0

DOWNLOADS

-  [Giant -Cal TB 117-2013](#)
 [Giant - BS5852 source 0](#)
 [Giant -Cal TB 117-2013](#)
 [Giant-Tongue Tear D2261-21811](#)
 [Giant -FMVSS302](#)
 [Giant - BS5852 source 0](#)
 [Giant -NFPA 260_UFAC](#)
-  [Giant-Breaking Strength-21811](#)
 [Giant-Seam Slip D4034-21811](#)
 [Giant -NFPA 260_UFAC](#)
 [Giant – FibreGuard report](#)
 [Giant EN 1021-1](#)
 [Giant -FMVSS302](#)

