

COLLECTION: HEARTLAND

DESIGN: HEARTLAND

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	38
Tariff item number	6001920000	MID	CNJIABRI366TON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	23
Full roll diameter inch	9.06	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments iron on reverse side

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

COLLECTION: HEARTLAND

DESIGN: HEARTLAND

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	No	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	8.85
Construction	Knitted	Useable width cm	140
Useable width inch	55.12	Full width cm	142
Full width inch	55.91	Weight g/m ²	452
Thickness mm	1.080	Colouring type	Piece dyed
Filament or staple	100% filament	Textured or non textured	100% not textured
Knitted	Yes		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Pile	Yes
------	-----

COLLECTION: HEARTLAND

DESIGN: HEARTLAND

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	5
Wyzenbeek double rubs	100,000	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering - ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	86	Tearing strength weft N	70
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	510	Tensile strength weft N/5cm	640
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	22.5	Elongation weft %	17
-------------------	------	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.21	Dimensional change warp after ironing with steam	0.27
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-0.08
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.00

COLLECTION: HEARTLAND

DESIGN: HEARTLAND

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.33	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.10	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.05	Dimensional change warp after ironing	0.07
Dimensional change weft	-1.26	Dimensional change weft after ironing	-1.19
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.03	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.26	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	5		

COLLECTION: HEARTLAND

DESIGN: HEARTLAND

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	75D	Warp Textured	No
Warp Threads per cm	20	Warp TPM	74

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	36F	Weft Textured	No
Weft Threads per cm	20	Weft TPM	144

DOWNLOADS

-  [Heartland](#)
-  [FG Stains Heartland](#)
-  [Heartland – FibreGuard report](#)

-  [Heartland-Cal TB 117-2013-26216](#)
-  [Heartland-NFPA 260 UFAC-26216](#)
-  [Heartland – FibreGuard report](#)

