

COLLECTION: INDIANA

DESIGN: INDIANA

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	28
Tariff item number	5407730000	MID	TRKET40IST
Country of origin	Turkey	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	10.63	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Accessories	Yes
------------	-----	-------------	-----

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: INDIANA

DESIGN: INDIANA

FABRIC SPECIFICATIONS

Composition	43% Recycled Polypropylene, 35% Polypropylene, 17% Recycled Polyester, 5% Polyester	Average yarn number	7.88
Construction	16x20	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	457	Thickness mm	2.400
Colouring type	Yarn dyed	Filament or staple	100% filament
Textured or non textured	100% textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: INDIANA

DESIGN: INDIANA

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	6
Pilling	4	Brush pilling	4-5
Wyzenbeek wire screen double rubs	100,000	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light – ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	136	Tearing strength weft N	220
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1600	Tensile strength weft N/5cm	660
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	43.5	Elongation weft %	25.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	-0.47
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	-0.27	Dimensional change weft after ironing without steam	-0.07

COLLECTION: INDIANA

DESIGN: INDIANA

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.40	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.46	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.23	Dimensional change warp after ironing	-0.67
Dimensional change weft	-2.25	Dimensional change weft after ironing	-1.72
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-3.60	Dimensional change warp after ironing	0.00
Dimensional change weft	-5.40	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.15	Dimensional change warp after ironing	-7.36
Dimensional change weft	-7.68	Dimensional change weft after ironing	-7.36
Colour fastness ISO 105 D01	4-5		

COLLECTION: INDIANA

DESIGN: INDIANA

CONSTRUCTION

Yarn 1

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	450 den	Warp Textured	Yes
Warp Threads per cm	16	Warp TPM	0

Yarn 2

Weft Composition	100% Polypropylene	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	1540 den	Weft Textured	Yes
Weft Threads per cm	10	Weft TPM	0

Yarn 3

Weft Composition	89% Recycled Polypropylene, 11% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	0.9 NM	Weft Textured	Yes
Weft Threads per cm	10	Weft TPM	0

DOWNLOADS

- [Indiana-FMVSS302-43441](#)
- [Indiana BS5825 Source 0](#)
- [Indiana FMVSS 302](#)
- [Indiana - FibreGuard report](#)
- [Indiana-NFPA 260_UFAC-43441](#)

- [Indiana NFPA 701](#)
- [Indiana-Cal TB 117-2013-43441](#)
- [Indiana BS5852](#)
- [Indiana NFPA 260](#)



