

Full technical product specifications (TPS) for this design

COLLECTION: INNOVATION

DESIGN: INNOVATION

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	30
Tariff item number	5801360000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	26.50	Vertical repeat inch	10.43
Horizontal repeat cm	23.20	Horizontal repeat inch	9.13
Face in	Yes	Full roll diameter cm	26
Full roll diameter inch	10.24	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments iron on reverse side

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

Full technical product specifications (TPS) for this design

COLLECTION: INNOVATION

DESIGN: INNOVATION

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
EN 1021-2 (with treatment)	Yes	FMVSS 302	Yes
NFPA 260	Yes	NFPA 701	No

FABRIC SPECIFICATIONS

Composition	75% Recycled Polyester, 25% Polyester	Average yarn number	32.9
Construction	108.27x25.98	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	408	Thickness mm	1.880
Colouring type	Piece dyed	Filament or staple	100% filament
Textured or non textured	100% Textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: INNOVATION

DESIGN: INNOVATION

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	7-8
Wyzenbeek double rubs	78,800	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	78,800	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	7-8
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	125	Tearing strength weft N	68
-------------------------	-----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1300	Tensile strength weft N/5cm	1500
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	53	Elongation weft %	20.5
-------------------	----	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.07	Dimensional change warp after ironing with steam	-0.67
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	-0.13

COLLECTION: INNOVATION

DESIGN: INNOVATION

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.35	Dimensional change warp after ironing	-1.19
Dimensional change weft	-0.59	Dimensional change weft after ironing	-0.59
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.43	Dimensional change warp after ironing	-3.23
Dimensional change weft	-1.35	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.32	Dimensional change warp after ironing	-1.06
Dimensional change weft	-0.99	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 D01	4-5		

COLLECTION: INNOVATION

DESIGN: INNOVATION

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	65/36/500	Warp Textured	Yes
Warp Threads per cm	108.27	Warp TPM	0

Yarn 2

Weft Composition	60% Polyester, 40% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300/288/450	Weft Textured	Yes
Weft Threads per cm	12.99	Weft TPM	0

Yarn 3

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	6.3NM	Weft Textured	Yes
Weft Threads per cm	12.99	Weft TPM	0

DOWNLOADS

- | | |
|--|--|
|  Innovation FMVSS 302 |  Innovation 23061150A Bru Textiles BS 5852 Source 0 |
|  Innovation - FibreGuard report |  INNOVATION-Cal TB 117-2013-41496 |
|  INNOVATION-NFPA 260_UFAC-41496 |  INNOVATION-FMVSS302-41496 |