

COLLECTION: OVERLAND

DESIGN: INSIGNA

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	9
Tariff item number	5407930000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Jacquard
Vertical repeat cm	2.50	Vertical repeat inch	0.98
Horizontal repeat cm	3.50	Horizontal repeat inch	1.38
Face in	Yes	Full roll diameter cm	24
Full roll diameter inch	9.45	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

COLLECTION: OVERLAND

DESIGN: INSIGNA

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	FMVSS 302	Yes
NFPA 260	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	10.73
Construction	32.28x16.53	Woven	Yes
Useable width cm	142	Useable width inch	55.91
Full width cm	144	Full width inch	56.69
Weight g/m²	455	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	54% filament, 46% staple
Textured or non textured	54% textured, 46% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Reactive	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: OVERLAND

DESIGN: INSIGNA

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Colour fastness to light	5
Wyzenbeek double rubs	200,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type general upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	140	Tearing strength weft N	120
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1800	Tensile strength weft N/5cm	1200
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	37,50	Elongation weft %	18,50
-------------------	-------	-------------------	-------

Seam slippage – ISO 13936-2

Seam slippage warp mm	5	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing with steam	0.33
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-0.08
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.00

COLLECTION: OVERLAND

DESIGN: INSIGNA

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.97	Dimensional change warp after ironing	-2.01
Dimensional change weft	-1.99	Dimensional change weft after ironing	-1.96
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.44	Dimensional change warp after ironing	-3.56
Dimensional change weft	-2.98	Dimensional change weft after ironing	-3.01
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.53	Dimensional change warp after ironing	-1.69
Dimensional change weft	-1.83	Dimensional change weft after ironing	-1.69
Colour fastness ISO 105 D01	5		

COLLECTION: OVERLAND

DESIGN: INSIGNA

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	300/450	Warp Textured	Yes
Warp Threads per cm	16.14	Warp TPM	0

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2/10	Warp Textured	No
Warp Threads per cm	16.14	Warp TPM	0

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300D/96	Weft Textured	Yes
Weft Threads per cm	8.27	Weft TPM	0

Yarn 4

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1250D	Weft Textured	No
Weft Threads per cm	5.51	Weft TPM	0

Yarn 5

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1200D	Weft Textured	Yes
Weft Threads per cm	2.75	Weft TPM	0

DOWNLOADS

-  [Insigna – FibreGuard report](#)
-  [Insigna-NFPA 260_UFAC](#)
-  [Insigna-Cal TB 117-2013](#)

-  [Overland - BS5852 source 0](#)
-  [Overland - BS5852 source 0 \(1\)](#)
-  [Insigna-FMVSS302](#)



