

Full technical product specifications (TPS) for this design

COLLECTION: KEYSTONE

DESIGN: KEYSTONE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	35
Tariff item number	5211310090	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	23.5
Full roll diameter inch	9.25	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

There are no technical details for this section.

COLLECTION: KEYSTONE

DESIGN: KEYSTONE

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	EN 1021-1	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	79% Cotton, 21% Polyester	Average yarn number	6.79
Construction	14.17x9.06	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	342	Thickness mm	0.850
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Sanforized	Yes	Stenter	Yes
------------	-----	---------	-----

Type of print or dye

Reactive	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: KEYSTONE

DESIGN: KEYSTONE

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	4
Wyzenbeek double rubs	20,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	20,000	Wyzenbeek cotton duck type unrated	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	4-5
--------------------------	-----

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	62	Tearing strength weft N	91
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1400	Tensile strength weft N/5cm	790
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	17	Elongation weft %	16
-------------------	----	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	-0.07

COLLECTION: KEYSTONE

DESIGN: KEYSTONE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.10	Dimensional change warp after ironing	-1.99
Dimensional change weft	-2.23	Dimensional change weft after ironing	-2.00
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.92	Dimensional change warp after ironing	-2.32
Dimensional change weft	-2.52	Dimensional change weft after ironing	-2.32
Colour fastness ISO 105 D01	5		

COLLECTION: KEYSTONE

DESIGN: KEYSTONE

CONSTRUCTION

Yarn 1

Warp Composition	79% Cotton, 21% Polyester	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	1100D	Warp Textured	No
Warp Threads per cm	14.17	Warp TPM	0

Yarn 2

Weft Composition	79% Cotton, 21% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1100D	Weft Textured	No
Weft Threads per cm	9.06	Weft TPM	0

DOWNLOADS

-  [Keystone-FMVSS302](#)
-  [Keystone-NFPA 260 UFAC](#)
-  [Keystone – FibreGuard report](#)
-  [Keystone EN 1021-1](#)
-  [Keystone-Cal TB 117-2013](#)
-  [Keystone BS 5852 Source 0](#)
-  [Keystone – FibreGuard report](#)

