

COLLECTION: LINIQUE

DESIGN: LINIQUE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	26
Tariff item number	5407730000	MID	TRKET40IST
Country of origin	Turkey	Characteristics	Texture
Vertical repeat cm	13.00	Vertical repeat inch	5.12
Horizontal repeat cm	24.00	Horizontal repeat inch	9.45
Face in	Yes	Full roll diameter cm	28
Full roll diameter inch	11.02	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

COLLECTION: LINIQUE

DESIGN: LINIQUE

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
EN 1021-1	Yes	FMVSS 302	No
NFPA 260	Yes		

FABRIC SPECIFICATIONS

40% Recycled Polyester, 36% Recycled Polypropylene, 24%			
Composition	Acrylic	Average yarn number	5.31
Construction	18.4x8.01	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m²	497	Thickness mm	2.540
Colouring type	Yarn dyed	Filament or staple	100% Filament
Textured or non textured	100% Textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Thermofixed	Yes	Airo	Yes
Stenter	Yes		

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: LINIQUE

DESIGN: LINIQUE

MECHANICAL PERFORMANCE

Martindale rubs	70,000	Colour fastness to light	6
Wyzenbeek double rubs	96,300	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	96,300	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	410	Tearing strength weft N	130
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1200	Tensile strength weft N/5cm	1800
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	47.5	Elongation weft %	39.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.20
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.13

COLLECTION: LINIQUE

DESIGN: LINIQUE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.72	Dimensional change warp after ironing	-1.52
Dimensional change weft	-1.52	Dimensional change weft after ironing	-1.32
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.57	Dimensional change warp after ironing	-3.44
Dimensional change weft	-3.54	Dimensional change weft after ironing	-3.31
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-8.07	Dimensional change warp after ironing	-1.72
Dimensional change weft	-1.92	Dimensional change weft after ironing	-1.72
Colour fastness ISO 105 D01	5		

COLLECTION: LINIQUE

DESIGN: LINIQUE

CONSTRUCTION

Yarn 1

Warp Composition	100% Solution Dyed Recycled Polypropylene	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	1200 Den	Warp Textured	Yes
Warp Threads per cm	18.4	Warp TPM	0

Yarn 2

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	500 Den	Weft Textured	Yes
Weft Threads per cm	2.67	Weft TPM	0

Yarn 3

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	2000 Den	Weft Textured	Yes
Weft Threads per cm	2.67	Weft TPM	0

Yarn 4

Weft Composition	52% Acrylic, 48% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	1.5 NM	Weft Textured	Yes
Weft Threads per cm	2.67	Weft TPM	410

DOWNLOADS

-  [LINIQUE-FMVSS302-50698 FAIL](#)
-  [LINIQUE-NFPA 260_24-50698](#)
-  [LINIQUE-Cal TB 117-2013-50698](#)

-  [Linique EN 1021-1](#)
-  [Linique BS5825 Source 0](#)