

COLLECTION: MONSIEUR

DESIGN: MONSIEUR

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	35
Tariff item number	5801360000	MID	TRKET40IST
Country of origin	Turkey	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	32
Full roll diameter inch	12.6	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE CODES



CARE AND USAGE

Care code comments	iron on reverse side	Type of finish	tumbled
--------------------	----------------------	----------------	---------

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



**STANDARD
100**
0611045
Centexbel



Labels

There are no technical details for this section.

COLLECTION: MONSIEUR

DESIGN: MONSIEUR

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	No	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	57% Acrylic, 43% Polyester	Average yarn number	18.71
Construction	14x70	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	449	Thickness mm	1.520
Colouring type	Yarn dyed	Filament or staple	59% staple + 41% filament
Textured or non textured	100% textured	Finish type	tumbled

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

There are no technical details for this section.

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: MONSIEUR

DESIGN: MONSIEUR

MECHANICAL PERFORMANCE

Martindale rubs	25,000	Colour fastness to light	4
Wyzenbeek double rubs	30,000	Pilling	4-5
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	30,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen medium duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	100	Tearing strength weft N	100
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1900	Tensile strength weft N/5cm	1100
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	39.5	Elongation weft %	29.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	5	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.21	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	-0.07	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	-0.33	Dimensional change weft after ironing without steam	0.00

COLLECTION: MONSIEUR

DESIGN: MONSIEUR

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.03	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.07	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-0.66	Dimensional change warp after ironing	-0.66
Dimensional change weft	-0.83	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.63	Dimensional change warp after ironing	-0.53
Dimensional change weft	-0.60	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 D01	5		

COLLECTION: MONSIEUR

DESIGN: MONSIEUR

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	157 den	Warp Textured	Yes
Warp Threads per cm	70	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	500 den	Weft Textured	Yes
Weft Threads per cm	10	Weft TPM	0

Yarn 3

Weft Composition	100% Acrylic	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	1.5 NM	Weft Textured	Yes
Weft Threads per cm	4	Weft TPM	0

DOWNLOADS

 [Monsieur – FibreGuard report](#)

 [Monsieur-Cal TB 117-2013](#)

 [Monsieur BS 5852 Source 0](#)

 [Monsieur-NFPA 260_UFAC](#)

