

COLLECTION: NOLITA

DESIGN: NOLITA

## BASIC INFORMATION

|                              |            |                                     |                |
|------------------------------|------------|-------------------------------------|----------------|
| Brand                        | FibreGuard | Number of colour ways               | 33             |
| Tariff item number           | 5407920000 | MID                                 | INDDEEXP167MUM |
| Country of origin            | India      | Characteristics                     | Flat Weave     |
| Vertical repeat cm           | Plain      | Vertical repeat inch                | Plain          |
| Horizontal repeat cm         | Plain      | Horizontal repeat inch              | Plain          |
| Face in                      | Yes        | Full roll diameter cm               | 19             |
| Full roll diameter inch      | 7.48       | Average piece length m              | 50             |
| Minimum for special colour m | 1000       | Delivery time weeks special lab dip | 2              |

## CARE CODES



## CARE AND USAGE

Type of finish stenter + chints

### Use codes

|             |     |                        |     |
|-------------|-----|------------------------|-----|
| Curtains    | Yes | Curtains and draperies | Yes |
| Upholstery  | Yes | Bed covering           | Yes |
| Accessories | Yes |                        |     |

## ENVIRONMENTAL STANDARDS



STANDARD  
100  
0611045  
Centexbel



### Labels

There are no technical details for this section.

COLLECTION: NOLITA

DESIGN: NOLITA

## FR STANDARDS

|                  |     |          |     |
|------------------|-----|----------|-----|
| BS 5852 Source 0 | Yes | CAL 117  | Yes |
| FMVSS 302        | No  | NFPA 260 | Yes |

## FABRIC SPECIFICATIONS

|                          |                           |                     |                          |
|--------------------------|---------------------------|---------------------|--------------------------|
| Composition              | 97% Polyester, 3% Viscose | Average yarn number | 11.44                    |
| Construction             | 21.2x20.1                 | Woven               | Yes                      |
| Useable width cm         | 138                       | Useable width inch  | 54.33                    |
| Full width cm            | 140                       | Full width inch     | 55.12                    |
| Weight g/m <sup>2</sup>  | 361                       | Thickness mm        | 0.000                    |
| Colouring type           | Piece dyed                | Filament or staple  | 84% filament, 16% staple |
| Textured or non textured | 100% not textured         | Finish type         | stenter + chints         |

### Treatment

|                       |     |
|-----------------------|-----|
| Stain free technology | Yes |
|-----------------------|-----|

### Type of finish

There are no technical details for this section.

### Type of print or dye

|          |     |          |     |
|----------|-----|----------|-----|
| Disperse | Yes | Reactive | Yes |
|----------|-----|----------|-----|

### Weaving type

|       |     |
|-------|-----|
| Dobby | Yes |
|-------|-----|

COLLECTION: NOLITA

DESIGN: NOLITA

## MECHANICAL PERFORMANCE

|                                   |         |                                             |        |
|-----------------------------------|---------|---------------------------------------------|--------|
| Martindale rubs                   | 100,000 | Colour fastness to light                    | 4-5    |
| Wyzenbeek double rubs             | 140,000 | Pilling                                     | 4      |
| Brush pilling                     | 4       | Wyzenbeek wire screen double rubs           | 15,000 |
| Wyzenbeek cotton duck double rubs | 140,000 | Wyzenbeek cotton duck type heavy upholstery | Yes    |
| Wyzenbeek wire screen heavy duty  | Yes     |                                             |        |

### Colour fastness to light – ISO 105-B02

|                          |     |
|--------------------------|-----|
| Colour fastness to light | 4-5 |
|--------------------------|-----|

### Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

### Colour fastness to water – ISO 105-E01

|                          |   |
|--------------------------|---|
| Colour fastness to water | 5 |
|--------------------------|---|

### Colour fastness to dry rub – ISO 105-X12

|                         |     |
|-------------------------|-----|
| Colour fastness dry rub | 4-5 |
|-------------------------|-----|

### Colour fastness to wet rub – ISO 105-X12

|                         |     |
|-------------------------|-----|
| Colour fastness wet rub | 4-5 |
|-------------------------|-----|

### Tearing strength – ISO 13937-3

|                         |     |                         |    |
|-------------------------|-----|-------------------------|----|
| Tearing strength warp N | 100 | Tearing strength weft N | 57 |
|-------------------------|-----|-------------------------|----|

### Tensile strength – ISO 13934-1

|                             |     |                             |     |
|-----------------------------|-----|-----------------------------|-----|
| Tensile strength warp N/5cm | 700 | Tensile strength weft N/5cm | 910 |
|-----------------------------|-----|-----------------------------|-----|

### Elongation – ISO 13934-1

|                   |      |                   |    |
|-------------------|------|-------------------|----|
| Elongation warp % | 38.5 | Elongation weft % | 38 |
|-------------------|------|-------------------|----|

### Seam slippage – ISO 13936-2

|                       |   |                       |   |
|-----------------------|---|-----------------------|---|
| Seam slippage warp mm | 3 | Seam slippage weft mm | 4 |
|-----------------------|---|-----------------------|---|

### Dimensional stability (indicated in %) – ISO 3759

|                                                     |      |                                                     |       |
|-----------------------------------------------------|------|-----------------------------------------------------|-------|
| Dimensional change warp                             | 0.00 | Dimensional change warp after ironing with steam    | -1.54 |
| Dimensional change warp after ironing without steam | 0.07 | Dimensional change weft                             | 0.00  |
| Dimensional change weft after ironing with steam    | 1.27 | Dimensional change weft after ironing without steam | 0.13  |

COLLECTION: NOLITA

DESIGN: NOLITA

## ACOUSTICS

### Sound absorption performance for drapery

There are no technical details for this section.

### Sound absorption performance for upholstery

There are no technical details for this section.

### Sound transmission

There are no technical details for this section.

## WASHABILITY

### Resistance to domestic washing 30° C, indicated in % - ISO 6330

|                             |       |                                       |       |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional change warp     | -0.53 | Dimensional change warp after ironing | -0.53 |
| Dimensional change weft     | -0.10 | Dimensional change weft after ironing | 0.07  |
| Colour fastness ISO 105 C06 | 4-5   |                                       |       |

### Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

### Resistance to domestic washing 60°C, indicated in % - ISO 6330

|                             |       |                                       |       |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional change warp     | -2.51 | Dimensional change warp after ironing | -2.52 |
| Dimensional change weft     | 0.63  | Dimensional change weft after ironing | 0.66  |
| Colour fastness ISO 105 C06 | 4-5   |                                       |       |

### Resistance to domestic washing 74 C ISO 6330

|                         |      |                                       |      |
|-------------------------|------|---------------------------------------|------|
| Dimensional change warp | 0.00 | Dimensional change warp after ironing | 0.00 |
| Dimensional change weft | 0.00 | Dimensional change weft after ironing | 0.00 |

### Resistance to dry cleaning P, indicated in % - ISO 105 D01

|                             |       |                                       |      |
|-----------------------------|-------|---------------------------------------|------|
| Dimensional change warp     | -1.06 | Dimensional change warp after ironing | 0.46 |
| Dimensional change weft     | 0.50  | Dimensional change weft after ironing | 0.46 |
| Colour fastness ISO 105 D01 | 5     |                                       |      |

COLLECTION: NOLITA

DESIGN: NOLITA

## CONSTRUCTION

### Yarn 1

|                           |                |                  |     |
|---------------------------|----------------|------------------|-----|
| Warp Composition          | 100% Polyester | Warp Is Filament | Yes |
| Warp Is Not High Tenacity | Yes            | Warp Is Staple   | No  |
| Warp Sizes                | 450 den        | Warp Textured    | No  |
| Warp Threads per cm       | 21.2           | Warp TPM         | 550 |

### Yarn 2

|                           |                |                  |     |
|---------------------------|----------------|------------------|-----|
| Weft Composition          | 59% Polyester, | Weft Is Filament | Yes |
| Weft Is Not High Tenacity | Yes            | Weft Is Staple   | No  |
| Weft Sizes                | 6nm            | Weft Textured    | No  |
| Weft Threads per cm       | 6.8            | Weft TPM         | 600 |

### Yarn 3

|                           |                |                  |     |
|---------------------------|----------------|------------------|-----|
| Weft Composition          | 100% Polyester | Weft Is Filament | Yes |
| Weft Is Not High Tenacity | Yes            | Weft Is Staple   | No  |
| Weft Sizes                | 450 den        | Weft Textured    | No  |
| Weft Threads per cm       | 13.3           | Weft TPM         | 550 |

## DOWNLOADS

[Nolita – FibreGuard report](#)
[Nolita-Cal TB 117-2013](#)
[Nolita-FMVSS302](#)
[Nolita BS5852 source 0](#)
[Nolita-NFPA 260 UFAC](#)
