

COLLECTION: PERFECTO

DESIGN: PERFECTO

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	60
Tariff item number	5801360000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	26
Full roll diameter inch	10.24	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments iron on reverse side

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65 Yes

COLLECTION: PERFECTO

DESIGN: PERFECTO

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
EN 1021-1	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	36% Polyester, 32% Cotton, 22% Viscose, 10% Linen	Average yarn number	4.66
Construction	13x7	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	429	Thickness mm	1.040
Colouring type	Piece dyed	Filament or staple	74% staple + 26% filament
Textured or non textured	100% not textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

There are no technical details for this section.

Weaving type

Dobby	Yes
-------	-----

COLLECTION: PERFECTO

DESIGN: PERFECTO

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	5
Wyzenbeek double rubs	110,000	Pilling	4
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	110,000
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	44	Tearing strength weft N	78
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1100	Tensile strength weft N/5cm	630
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	16.5	Elongation weft %	19.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	5
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.14	Dimensional change warp after ironing with steam	-0.60
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	-0.07	Dimensional change weft after ironing without steam	0.00

COLLECTION: PERFECTO

DESIGN: PERFECTO

ACOUSTICS

Sound absorption performance for drapery

Weighted Sound Absorption Coefficient (α_w) – ISO 11654	0.65	Weighted Sound Absorption Coefficient (α_w) – Class – ISO 11654	C
Sound Absorption Average ($\bar{\alpha}$) – ASTM C423	0.74	Noise Reduction Coefficient (NRC) – ASTM C423	0.8

Sound absorption performance for upholstery

Weighted Sound Absorption Coefficient (α_w) – ISO 11654	0.75	Weighted Sound Absorption Coefficient (α_w) – Class – ISO 11654	C
Sound Absorption Average ($\bar{\alpha}$) – ASTM C423	0.68	Noise Reduction Coefficient (NRC) – ASTM C423	0.7

Sound transmission

Weighted Sound Reduction Index (RW) – ISO 717-1	5	Sound Transmission Class (STC) – ASTM E413	4
---	---	--	---

WASHABILITY

Resistance to domestic washing 30° C, indicated in % – ISO 6330

Dimensional change warp	-6.00	Dimensional change warp after ironing	-4.84
Dimensional change weft	-0.73	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % – ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % – ISO 6330

Dimensional change warp	-8.35	Dimensional change warp after ironing	-8.42
Dimensional change weft	-1.86	Dimensional change weft after ironing	-1.86
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % – ISO 105 D01

Dimensional change warp	-4.21	Dimensional change warp after ironing	-1.46
Dimensional change weft	-1.82	Dimensional change weft after ironing	-1.46
Colour fastness ISO 105 D01	4-5		

COLLECTION: PERFECTO

DESIGN: PERFECTO

CONSTRUCTION

Yarn 1

Warp Composition	30% Linen, 70% Viscose	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2/6 Ne	Warp Textured	No
Warp Threads per cm	6.5	Warp TPM	NA

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	5 Nm	Weft Textured	No
Weft Threads per cm	7	Weft TPM	NA

Yarn 3

Warp Composition	100% Cotton	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2/6 Ne	Warp Textured	No
Warp Threads per cm	6.5	Warp TPM	NA

DOWNLOADS

-  [Perfecto - FibreGuard report](#)
-  [Perfecto BS 5852 Source 0](#)
-  [Perfecto EN 1021-1](#)
-  [Perfecto-Cal TB 117-2013](#)
-  [Perfecto - Cal TB 117-2013](#)

-  [Perfecto - NFPA 260 UFAC](#)
-  [Perfecto - FMVSS302](#)
-  [202501768-Acoustic_Perfecto](#)
-  [Perfecto - FibreGuard report](#)



Full technical product specifications (TPS) for this design

COLLECTION: PERFECTO

DESIGN: PERFECTO