

COLLECTION: QUILVET

DESIGN: PIA

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	8
Tariff item number	6001920000	MID	CNJIABRI366TON
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	5.50	Vertical repeat inch	2.17
Horizontal repeat cm	3.30	Horizontal repeat inch	1.30
Face in	Yes	Full roll diameter cm	30
Full roll diameter inch	11.81	Average piece length m	20
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

COLLECTION: QUILVET

DESIGN: PIA

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	No
CAL 117	Yes	FMVSS 302	Yes
NFPA 260	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	17.43
Composition fabric	100% Polyester	Composition backing	100% Polyester
Construction	knitted	Useable width cm	138
Useable width inch	54.33	Full width cm	140
Full width inch	55.12	Weight g/m ²	803
Thickness mm	2.990	Colouring type	Piece dyed
Water repellent	Yes	Water repellent specification	2-3
Filament or staple	100% Filament	Textured or non textured	100% Not textured
Knitted	Yes		

Treatment

Backing	Yes	Stain free technology	Yes
---------	-----	-----------------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Pile	Yes
------	-----

COLLECTION: QUILVET

DESIGN: PIA

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	4
Wyzenbeek double rubs	200,000	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	200,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Water repellent	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light – ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	100	Tearing strength weft N	140
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	780	Tensile strength weft N/5cm	650
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	30.5	Elongation weft %	18.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.52	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	-0.07	Dimensional change weft after ironing without steam	0.13

COLLECTION: QUILVET

DESIGN: PIA

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.06	Dimensional change warp after ironing	-1.59
Dimensional change weft	-2.06	Dimensional change weft after ironing	-1.40
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-4.38	Dimensional change warp after ironing	-4.45
Dimensional change weft	-2.63	Dimensional change weft after ironing	-2.52
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-4.18	Dimensional change warp after ironing	-2.13
Dimensional change weft	-2.03	Dimensional change weft after ironing	-2.13
Colour fastness ISO 105 D01	4-5		

COLLECTION: QUILVET

DESIGN: PIA

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	150D	Warp Textured	No
Warp Threads per cm	50	Warp TPM	300

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	105D	Warp Textured	No
Warp Threads per cm	90	Warp TPM	200

DOWNLOADS

-  [Quilvet-NFPA 260_UFAC-19478](#)
-  [Quilvet-FMVSS302-19478](#)
-  [Pia BS 5852 Source 0](#)
-  [Quilvet-Cal TB 117-2013-19478](#)
-  [Pia – FibreGuard report](#)
-  [Pia -Quilvet BS 5852 Source 0](#)

