

COLLECTION: PINDRIVE

DESIGN: PINDRIVE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	30
Tariff item number	5801370000	MID	CNSUZFUR88SUZ
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	10.63	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer	Yes	Prop 65	Yes
-------------------	-----	---------	-----

COLLECTION: PINDRIVE

DESIGN: PINDRIVE

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes

FABRIC SPECIFICATIONS

Composition	96% Recycled Polyester, 4% Polyamide	Average yarn number	22.42
Construction	27x47	Woven	Yes
Useable width cm	143	Useable width inch	56.3
Full width cm	145	Full width inch	57.09
Weight g/m ²	330	Thickness mm	1.830
Colouring type	Piece dyed	Filament or staple	100% filament
Textured or non textured	100% textured		

Treatment

Backing	Yes	Stain free technology	Yes
---------	-----	-----------------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: PINDRIVE

DESIGN: PINDRIVE

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	6
Wyzenbeek double rubs	100,000	Pilling	5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	113	Tearing strength weft N	110
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	770	Tensile strength weft N/5cm	710
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	32	Elongation weft %	36
-------------------	----	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.07
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.00

COLLECTION: PINDRIVE

DESIGN: PINDRIVE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.13	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.13	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-0.93	Dimensional change warp after ironing	-0.99
Dimensional change weft	-0.36	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-2.60	Dimensional change warp after ironing	0.00
Dimensional change weft	-1.00	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.83	Dimensional change warp after ironing	0.13
Dimensional change weft	-0.10	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 D01	4-5		

COLLECTION: PINDRIVE

DESIGN: PINDRIVE

CONSTRUCTION

Yarn 1

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	150D	Warp Textured	Yes
Warp Threads per cm	27	Warp TPM	0

Yarn 2

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	250D	Weft Textured	Yes
Weft Threads per cm	24	Weft TPM	0

Yarn 3

Weft Composition	80% Recycled Polyester, 20% Polyamide	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	320D	Weft Textured	Yes
Weft Threads per cm	23	Weft TPM	0

DOWNLOADS

-  [Pindrive-FMVSS302-44197](#)
-  [Pindrive - FibreGuard report](#)
-  [Pindrive-Cal TB 117-2013-44197](#)
-  [Pindrive-NFPA 260_UFAC-44197](#)
-  [Pindrive 24020961A Bru Textiles BS 5852 Source 0](#)

