

COLLECTION: STYLISE

DESIGN: STYLISE

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	35
Tariff item number	5801360000	MID	CNTONFOR1202TON
Country of origin	China	Characteristics	Chenille
Vertical repeat cm	26.00	Vertical repeat inch	10.24
Horizontal repeat cm	18.60	Horizontal repeat inch	7.32
Face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Care code comments iron on reverse side

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65 Yes

COLLECTION: STYLISE

DESIGN: STYLISE

FR STANDARDS

BS 5867 part 2 type B	No	BS 5852 Source 0	Yes
BS 5852 Source 1 (with treatment)	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes
NFPA 701	No		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	9.75
Construction	33x13.8	Woven	Yes
Useable width cm	145	Useable width inch	57.09
Full width cm	147	Full width inch	57.87
Weight g/m²	480	Thickness mm	1.160
Colouring type	Piece dyed	Filament or staple	66% staple + 34% filament
Textured or non textured	66% not etxured + 34% textured		

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Vat	Yes
-----	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: STYLISE

DESIGN: STYLISE

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	5-6
Wyzenbeek double rubs	60,000	Pilling	4-5
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	60,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	71	Tearing strength weft N	200
-------------------------	----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	1100
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	58.5	Elongation weft %	55
-------------------	------	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.17	Dimensional change warp after ironing with steam	-0.40
Dimensional change warp after ironing without steam	0.20	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	0.07

COLLECTION: STYLISE

DESIGN: STYLISE

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.23	Dimensional change warp after ironing	-1.13
Dimensional change weft	-0.36	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	3.05	Dimensional change warp after ironing	-2.78
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.68	Dimensional change warp after ironing	-0.79
Dimensional change weft	-0.93	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 D01	5		

COLLECTION: STYLISE

DESIGN: STYLISE

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	410D	Warp Textured	Yes
Warp Threads per cm	33	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	5.3S	Weft Textured	No
Weft Threads per cm	13.8	Weft TPM	0

DOWNLOADS

-  [Stylise - Anti-bacterial report ASTM E2149](#)
-  [Stylise BS 5852 Source 0](#)
-  [Stylise-NFPA 260 UFAC-33269](#)
-  [Stylise Bru Textiles BS 5852 Sources 0+1](#)
-  [Stylise - Anti-bacterial report ISO 20743](#)
-  [Stylise-FMVSS302-33269](#)
-  [Stylise - FibreGuard report](#)
-  [202101156-NFPA Stylise](#)
-  [Stylise-Cal TB 117-2013-33269](#)

