

COLLECTION: TONTO

DESIGN: TONTO

BASIC INFORMATION

Brand	Bru	Number of colour ways	35
Tariff item number	5211310090	MID	INGMKNI606MUM
Country of origin	India	Characteristics	Flat Weave
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	18
Full roll diameter inch	7.09	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Bed covering	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

FR STANDARDS

BS 5852 Source 0	Yes	CAL 117	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: TONTO

DESIGN: TONTO

FABRIC SPECIFICATIONS

Composition	58% Cotton, 42% Polyester	Average yarn number	14.44
Construction	18x22	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	277	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	89% staple + 11% filament
Textured or non textured	89% not textured + 11% textured		

Treatment

There are no technical details for this section.

Type of finish

Calender	Yes
----------	-----

Type of print or dye

Disperse	Yes	Reactive	Yes
----------	-----	----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: TONTO

DESIGN: TONTO

MECHANICAL PERFORMANCE

Martindale rubs	40,000	Colour fastness to light	4–5
Wyzenbeek double rubs	85,000	Pilling	3–4
Brush pilling	3–4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	85,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	4–5
--------------------------	-----

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	4–5
--------------------------	-----

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4–5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4–5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	33	Tearing strength weft N	52
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1400	Tensile strength weft N/5cm	620
-----------------------------	------	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	24.5	Elongation weft %	16.5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.14	Dimensional change warp after ironing with steam	–0.20
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.15
Dimensional change weft after ironing with steam	0.40	Dimensional change weft after ironing without steam	0.13

COLLECTION: TONTO

DESIGN: TONTO

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-3.00	Dimensional change warp after ironing	-3.00
Dimensional change weft	-0.73	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-4.81	Dimensional change warp after ironing	-4.52
Dimensional change weft	-1.00	Dimensional change weft after ironing	-0.80
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.79	Dimensional change warp after ironing	0.07
Dimensional change weft	0.10	Dimensional change weft after ironing	0.07
Colour fastness ISO 105 D01	4-5		

COLLECTION: TONTO

DESIGN: TONTO

CONSTRUCTION

Yarn 1

Warp Composition	52% Polyester, 48% Cotton	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2/12s	Warp Textured	No
Warp Threads per cm	18	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	240D	Weft Textured	Yes
Weft Threads per cm	11	Weft TPM	0

Yarn 3

Weft Composition	100% Cotton	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	8's	Weft Textured	No
Weft Threads per cm	11	Weft TPM	0

DOWNLOADS

-  [Tonto BS 5852 Source 0](#)
-  [Tonto -NFPA 260 UFAC-20903](#)

-  [Tonto -Cal TB 117-2013-20903](#)
-  [Tonto -FMVSS302-20903](#)

