

COLLECTION: TREZOR

DESIGN: TREZOR

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	33
Tariff item number	5801360000	MID	INDDEEXP167MUM
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	10.63	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel

ISO 14001
Environmental
Management

Labels

There are no technical details for this section.

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	EN 1021-2 (with treatment)	Yes
FMVSS 302	Yes	NFPA 260	Yes

COLLECTION: TREZOR

DESIGN: TREZOR

FABRIC SPECIFICATIONS

Composition	54% Polyester, 46% Cotton	Average yarn number	6.01
Construction	13.4x9	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	373	Thickness mm	0.980
Colouring type	Piece dyed	Filament or staple	100% Staple
Textured or non textured	100% Not Textured		

Treatment

Stain free technology	Yes
-----------------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Reactive	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: TREZOR

DESIGN: TREZOR

MECHANICAL PERFORMANCE

Martindale rubs	35,000	Colour fastness to light	5
Wyzenbeek double rubs	50,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	50,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light – ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	47	Tearing strength weft N	50
-------------------------	----	-------------------------	----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	720	Tensile strength weft N/5cm	700
-----------------------------	-----	-----------------------------	-----

Elongation – ISO 13934-1

Elongation warp %	16,5	Elongation weft %	26,5
-------------------	------	-------------------	------

Seam slippage – ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing with steam	-0.40
Dimensional change warp after ironing without steam	-0.07	Dimensional change weft	-0.21
Dimensional change weft after ironing with steam	0.40	Dimensional change weft after ironing without steam	0.20

COLLECTION: TREZOR

DESIGN: TREZOR

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.91	Dimensional change warp after ironing	-3.00
Dimensional change weft	-0.17	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-5.52	Dimensional change warp after ironing	-5.50
Dimensional change weft	-0.40	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.42	Dimensional change warp after ironing	-0.40
Dimensional change weft	-0.43	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 D01	5		

COLLECTION: TREZOR

DESIGN: TREZOR

CONSTRUCTION

Yarn 1

Warp Composition	100% Cotton	Warp Is Filament	No
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	2/10 carded cotton slub yarn	Warp Textured	No
Warp Threads per cm	13.4	Warp TPM	400

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	No
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	5NM	Weft Textured	No
Weft Threads per cm	9	Weft TPM	750

DOWNLOADS

-  [Trezor 18081005A Bru Textiles BS 5852 Source 0](#)
-  [Trezor – FibreGuard report](#)
-  [Trezor-Cal TB 117-2013](#)
-  [Trezor-NFPA 260_UFAC](#)
-  [Trezor-FMVSS302](#)

