

COLLECTION: WOOLSKIN

DESIGN: WOOLSKIN

BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	57
Tariff item number	5407920000	MID	INDDEHOM167MUM
Country of origin	India	Characteristics	Flat Weave
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	24
Full roll diameter inch	0	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE CODES



CARE AND USAGE

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel



Labels

Prop 65	Yes
---------	-----

COLLECTION: WOOLSKIN

DESIGN: WOOLSKIN

FR STANDARDS

BS 5852 Source 0	Yes	BS 5852 Source 1 (with treatment)	Yes
CAL 117	Yes	FMVSS 302	No
NFPA 260	Yes	NFPA 701	No

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	17.02
Construction	33.07x25.98	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	347	Thickness mm	0.800
Colouring type	Piece dyed	Filament or staple	100% filament
Textured or non textured	100% textured		

Treatment

Anti-bacterial/microbial	Yes	Mildew resistant	Yes
Odour resistant	Yes	Stain free technology	Yes

Type of finish

Calender	Yes
----------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: WOOLSKIN

DESIGN: WOOLSKIN

MECHANICAL PERFORMANCE

Martindale rubs	30,000	Colour fastness to light	4
Wyzenbeek double rubs	100,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	100,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to weathering - ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water - ISO 105-E01

Colour fastness to water	4-5
--------------------------	-----

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	120	Tearing strength weft N	120
-------------------------	-----	-------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	880	Tensile strength weft N/5cm	1300
-----------------------------	-----	-----------------------------	------

Elongation - ISO 13934-1

Elongation warp %	25.5	Elongation weft %	44
-------------------	------	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing with steam	0.33
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.08
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.20

COLLECTION: WOOLSKIN

DESIGN: WOOLSKIN

ACOUSTICS

Sound absorption performance for drapery

There are no technical details for this section.

Sound absorption performance for upholstery

There are no technical details for this section.

Sound transmission

There are no technical details for this section.

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.27	Dimensional change warp after ironing	-0.07
Dimensional change weft	-0.27	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.52	Dimensional change warp after ironing	-1.32
Dimensional change weft	-1.23	Dimensional change weft after ironing	-0.93
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	-2.00	Dimensional change warp after ironing	0.00
Dimensional change weft	-2.00	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.80	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.50	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	4-5		

COLLECTION: WOOLSKIN

DESIGN: WOOLSKIN

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	400D	Warp Textured	Yes
Warp Threads per cm	33.07	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	420D	Weft Textured	Yes
Weft Threads per cm	25.98	Weft TPM	0

DOWNLOADS

-  [Woolskin-Cal TB 117-2013-27266](#)
-  [Woolskin-NFPA 260_UFAC-27266](#)
-  [Woolskin - FibreGuard report](#)
-  [Woolskin - Anti-bacterial report](#)
-  [Woolskin Bru Textiles BS 5852 Source 0](#)

