

LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE

**Linear Low Density Polyethylene**

**HR3935U**

**Technical support:**  
 Polymer Technology Services Centre  
 22 Pressburg Road,  
 Modderfontein, 1645  
 South Africa

Tel: +27 (0)11 458 0700  
 Fax: +27 (0)11 458 0734

**Sales office:**  
 Sasol Base Chemicals  
 PO Box 5486  
 Johannesburg, 2000  
 South Africa

Tel: +27 (0) 10 344 5000  
 polymers@sasol.com

Date of issue: March 2017

www.sasol.com

**Melt Index: 3.5 g/10min**

**Density: 0.939 g/cm<sup>3</sup>**

**Features**

- High rigidity
- Excellent impact strength
- Excellent chemical resistance
- Good ESCR
- Heat and UV resistant
- Tough and abrasion resistant
- Colourable
- Hexene copolymer
- UV8 rating

**Applications**

- Rotational moulding of large items such as water tanks, chemical tanks and industrial products
- Injection moulding of large parts
- Outdoor use

**Additives**

- Antioxidant
- UV stabiliser
- Internal mould release

Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
<b>Resin Properties</b>	Melt Index (190°C/2.16kg)	3.5 g/10min	3.5 g/10min	ASTM D1238
	Nominal density	0.939 g/cm <sup>3</sup>	0.939 g/cm <sup>3</sup>	ASTM D1505
<b>Product Properties</b>	Tensile strength at yield	19 MPa	2755 psi	ASTM D638 <sup>1)</sup>
	Tensile strength at break	25 MPa	3625 psi	ASTM D638 <sup>1)</sup>
	Elongation at break	850 %	850 %	ASTM D638 <sup>1)</sup>
	Flexural modulus	800 MPa	116000 psi	ASTM D790
	ESCR	> 1000 hr	> 1000 hr	ASTM D1693 <sup>2)</sup>
	Impact energy at -40°C	30 J/mm	111 ft/lbs	ASTM D5628 <sup>3)</sup>
	Shore D hardness	61	61	ASTM D2240
Vicat softening temperature	120 °C	120 °C	ASTM D1525	


1) Crosshead speed 50 mm/min  
 2) 100% Igepal CO630  
 3) Tested on 5mm rotomoulded product

LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE

**Injection moulding**

MELT TEMPERATURE 200 - 240°C

M	°C	N	4	3	2	1	H
	300						
	260						
	220						
	180						
	140						
	100						
	60						
	20						



**Processing – Rotational moulding**

An air temperature of 270°C to 300°C is recommended for rotational moulding of HR3935U. Temperatures above 300°C should be avoided as this can narrow the processing window, and may result in poor physical properties. Due to the material's excellent heat resistance, it has very good colour stability, even in overcure conditions.

**Processing – Injection moulding**

HR3935U has a medium melt viscosity making it unsuitable for moulds with long flow paths. Typical melt temperatures are 200°C to 240°C. Parts can be demoulded at a relatively high temperature due to the material's high melting point and good rigidity.

**Handling**

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

**Storage**

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

**Combustibility**

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

**Regulatory & Legal Compliance**

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application.