

# PRODUCT DATA SHEET



LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE

## Linear Low Density Polyethylene

# HR3950

**Technical support:**  
 Polymer Technology Services  
 Centre  
 22 Pressburg Road,  
 Modderfontein, 1645  
 South Africa

Tel: +27 (0)11 458 0700  
 Fax: +27 (0)11 458 0734

**Sales office:**  
 Sasol Base Chemicals  
 PO Box 5486  
 Johannesburg, 2000  
 South Africa

Tel: +27 (0) 10 344 5000  
 polymers@sasol.com

Date of issue: March 2017

www.sasol.com

**Melt Index: 5.0 g/10min**

**Density: 0.939 g/cm<sup>3</sup>**

### Features

- High rigidity
- Good impact strength
- Excellent chemical resistance
- Good ESCR
- Tough and abrasion resistant
- Hexene copolymer

### Applications

- Rotational moulding of small to medium parts
- Injection moulding of large parts
- Indoor use

### Additives


- Antioxidant

Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
<b>Resin Properties</b>	Melt Index (190°C/2.16kg)	5.0 g/10min	5.0 g/10min	ASTM D1238
	Nominal density	0.939 g/cm <sup>3</sup>	0.939 g/cm <sup>3</sup>	ASTM D1505
<b>Product Properties</b>	Tensile strength at yield	20 MPa	2900 psi	ASTM D638 <sup>1)</sup>
	Tensile strength at break	27 MPa	3915 psi	ASTM D638 <sup>1)</sup>
	Elongation at break	900 %	900 %	ASTM D638 <sup>1)</sup>
	Flexural modulus	680 MPa	98600 psi	ASTM D790
	ESCR	> 1000 hr	> 1000 hr	ASTM D1693 <sup>2)</sup>
	Impact energy at -40°C	25 J/mm	92 ft/lbs	ASTM D5628 <sup>3)</sup>
	Shore D hardness	61	61	ASTM D2240
Vicat softening temperature	119 °C	119 °C	ASTM D1525	

- 1) Crosshead speed 50 mm/min
- 2) 100% Igepal CO630
- 3) Tested on 5mm rotomoulded product

LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE LLDPE

**Injection moulding**



**Processing – Rotational moulding**

An air temperature of 270°C to 300°C is recommended for rotational moulding of HR3950. Temperatures above 300°C should be avoided as this can narrow the processing window, and may result in poor physical properties. Due to the material’s excellent heat resistance, it has very good colour stability, even in overcure conditions.

**Processing – Injection moulding**

HR3950 has a medium melt viscosity making it unsuitable for moulds with long flow paths. Typical melt temperatures are 200°C to 240°C. Parts can be demoulded at a relatively high temperature due to the material’s high melting point and good rigidity.

**Handling**

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

**Storage**

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

**Combustibility**

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

**Regulatory & Legal Compliance**

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request. This material is not medically approved and should therefore not be used in any such application.

This publication contains information provided in good faith and is indicative, based on Sasol’s current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased or supplied by Sasol Chemicals are subject to the terms and conditions set out in the contract, order confirmation and/or bill of lading.