

PRODUCT DATA SHEET



SASOL

PP PP PP PP PP PP PP PP PP PP PP PP PP PP PP PP															
<h2>Polypropylene Homopolymer</h2>					Technical support: Polymer Technology Services Centre 22 Pressburg Road, Modderfontein, 1609 South Africa Tel: +27 (0)11 458 0700 Fax: +27 (0)11 458 0734					Sales office: Sasol Base Chemicals PO Box 5486 Johannesburg, 2000 South Africa Tel: +27 (0)10 344 5000 E-mail: polymers@sasol.com					
<h1>HMR127</h1>															

Date of issue: April 2017

www.sasol.com

MFR: 8.5 g/10min

Density: 0.905 g/cm³

Features

- Medium flow
- Specially formulated for processing on both cast and water quenched blown film lines
- Very good clarity
- Fast migrating slip agent
- Low tendency to block
- Good toughness

Applications

Extrusion

- Garment packaging
- Flower sleeves
- Food and confectionery packaging

Additives

- Antioxidant
- Processing stabiliser
- Acid scavenger
- Slip and Anti-block


Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
Resin Properties	Melt mass-flow rate – MFR (230/2.16)	8.5 g/10min	8.5 g/10min	ISO 1133
Film Properties (50µm water quenched blown film)	Gloss 20°	100	100	ASTM D2457
	Haze	2.5 %	2.5 %	ISO 14782
	Tensile strength at break – MD	44 MPa	6 380 psi	ISO 527-3
	Tensile strength at break – TD	40 MPa	5 800 psi	ISO 527-3
	Tensile strain at break – MD	700 %	700 %	ISO 527-3
	Tensile strain at break – TD	730 %	730 %	ISO 527-3
	Dart impact (F50)	300 g	300 g	ISO 7765-1
	Coefficient of friction (Static)	0.20	0.20	ISO 8295
Coefficient of friction (Dynamic)	0.17	0.17	ISO 8295	

The values quoted in the table were determined on film specimens produced to internal standards. The properties of film depends considerably on the processing conditions used. This aspect must be considered should the values be compared with properties of film produced using different conditions.




Typical processing conditions – HMR127

Blown film extrusion



Cast film extrusion



Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

Storage

As ultraviolet light may cause a change in material properties, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

Combustibility

Polypropylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polypropylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water, water mist being preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

Regulatory & Legal Compliance

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application.

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased from Sasol Chemicals are subject to the terms and conditions as set out in the contract, order confirmation and/or bill of lading.